

TRUSTARC™

KOBELCO

WELDING OF EUROPE



TRUSTARC DW-A55L ivaretar kravene i nye NORSOK M-101 Arctic 1, 2 og 3 og kombinerer dette med gode sveiseegenskaper og produktivitet i toppklasse.



© Equinor - Ole Jørgen Bratland.



© Equinor - Elisabeth Sahl.



© Equinor - Elisabeth Sahl.

SQL 1	NORSOK M-101 Arctic 1		NORSOK M-101 Arctic 2		NORSOK M-101 Arctic 3	
S420-S460	Testtemperatur	DW-A55L	Testtemperatur	DW-A55L	Testtemperatur	DW-A55L
SLAGSEIGHET > 42J	-50 °C	✓	-60 °C	✓	-60 °C	✓
CTOD > 0,25 mm	-20 °C	✓	-30 °C	✓	-40 °C	✓

The information contained or otherwise referenced herein is presented only as "typical" without guaranty or warranty. Typical data is obtained when welded and tested in accordance with EN or AWS standards. This data is intended to help the user choose the correct product. However, we do not assume any liability for correctness and information is subject to change without notice.

Kobelcos sortiment av lavlegerte rørtråder har kontrollert lavt hydrogeninnhold og ren overflate uten kobberbelegg.

www.kobelcowelding.nl